

Tepelné hodnoty, tepelná ochrana, tvárnice PORIT

Obj. hmotnost	Tepel. vodivost (W/mK) λ_R	Součinitel prostupu tepla U hodnota, (W/m ² K)									
		<i>při tloušťce zdi v cm</i>									
		5.0	7.5	10.0	11.5	15.0	17.5	20.0	24.0	30.0	36.5
0.35	0.09	-	-	-	-	-	0.45	0.40	0.34	0.28	0.23
0,35/0,40	0.10	1.22	0.94	0.76	0.68	0.55	0.49	0.44	0.37	0.31	0.25
0.40	0.11	1.30	1.00	0.82	0.73	0.59	0.54	0.48	0.41	0.33	0.28
0,50/0,55	0.12	1.36	1.06	0.87	0.78	0.64	0.58	0.52	0.44	0.36	0.30
0,50/0,55	0.13	1.42	1.12	0.92	0.83	0.68	0.62	0.55	0.47	0.39	0.32
0.55	0.14	1.48	1.17	0.97	0.88	0.72	0.66	0.59	0.50	0.41	0.35
0.60	0.15	1.54	1.22	1.02	0.92	0.76	0.69	0.62	0.53	0.44	0.37
0.60	0.16	1.59	1.27	1.06	0.97	0.80	0.73	0.66	0.56	0.47	0.39
0.70	0.21	1.80	1.48	1.26	1.16	0.97	0.90	0.82	0.71	0.59	0.50